

MODELING OF IONIZATION PHENOMENA IN SiC DIODES

by

Prof. Paolo Lugli
Dipartimento di Ingegneria Elettronica
Universita' di Roma "Tor Vergata"
Roma, ITALY


United State Army
EUROPEAN RESEARCH OFFICE
USARDSG-UK

CONTRACT NUMBER N68171-96-C-9115
R&D 8127-EE-01

3rd Interim Report
October 1997 - December 1997

The research reported in this document has been made possible through the support and sponsorship of the US government through its European Research Office of the U.S. Army. This report is intended for the internal management use of the Contractor and U.S. Government.

~~DISTRIBUTION STATEMENT C: Distribution authorized to U.S. Government
personnel and their contractors
requests for this document shall be referred to~~



19980710 125

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
<small>Public Reporting Burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204 Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.</small>				
1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE March. 3 rd , 1998	3. REPORT TYPE AND DATES COVERED Interim Report Oct.-Dec. 1997		
4. TITLE AND SUBTITLE MODELING OF IONIZATION PHENOMENA IN SiC DIODES		5. FUNDING NUMBERS C N68171-96-C-9115 PRWK2Q6C-8127-EE015		
6. AUTHOR(S) Prof. Paolo Lugli				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Universita' di Roma "Tor Vergata" Dipartimento della Ricerca Scientifica Via di Tor Vergata 00133 Roma ITALY		8. PERFORMING ORGANIZATION REPORT NUMBER 0003		
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) United State Army European Research Office USARDSG-UK		10. SPONSORING/MONITORING AGENCY REPORT NUMBER		
11. SUPPLEMENTARY NOTES				
12a. DISTRIBUTION/AVAILABILITY STATEMENT Public availability		12b. DISTRIBUTION CODE		
<p>13. ABSTRACT</p> <p>We have applied our drift-diffusion simulation to a 6H-SiC. We have first looked at the influence of temperature on device performance, in particular concerning the degree of ionization of the deep levels present in the semiconductor. We have detected large variations in the ionization rate by going when the temperature goes from 300 to 800 K. The different behavior of acceptors and donors causes the diode depletion region to grow more rapidly on the n side than on the p one. The peak field increases with temperature, due to the higher level of fixed charge at the junction. In the examined structures, tunneling times out of shallow are in the femtosecond range for sufficiently high fields. Thus tunneling is the dominant ionization mechanism under high bias conditions. We have studied the diode response to a pulsed voltage, finding a significant influence of tunneling processes. None of the effects found for SiC shows up in Si diodes. There, in fact, donors and acceptors are much shallower, and they result completely ionized under any standard operating condition.</p>				
14. SUBJECT TERMS SiC, Breakdown, ionization, devices		15. NUMBER OF PAGES		
		16. PRICE CODE		
17. SECURITY CLASSIFICATION OF REPORT	18. SECURITY CLASSIFICATION OF THIS PAGE	19. SECURITY CLASSIFICATION OF ABSTRACT	20. LIMITATION OF ABSTRACT	

NSN 7540-01-280-5500

Standard Form 298 (Rev. 1-69)
Prescribed by ANSI Std. Z39-18
298-102

Scientific work done during the reporting period

The work has continued along the lines indicated in the two previous reports. The Drift-Diffusion simulator has been used to study the dynamical behaviour of 6-H SiC diodes subject to a reverse bias pulse of picosecond duration.

In a Silicon diode, such condition creates a temporary current spike related to the dynamical rearrangement of carriers to the evolving potential. The spike rapidly decays away well before the end of the pulse, reaching the stationary condition typical of reverse bias, that is a current almost equal to zero.

In a 6H SiC diode, a quite peculiar situation is found. At sufficiently high bias (but lower than the breakdown voltage), after a very fast transient that leads to a spike similar to that of Si diodes, the current reaches a steady value different from zero, which values as high as 100 A/m². The current increases with reverse bias, leading to a knee in the reverse diode characteristics that are characterized by a very soft onset of breakdown. The phenomenon seems to be associated to the development of a dipole at the N-P⁺ interface, caused by the combined effect of field-assisted ionization and subsequent production of holes by impact ionization processes near that interface. When one of the two processes of field assisted ionization and impact ionization is selectively turned off in the simulation, a Silicon-like behaviour is found. This clearly indicates that the observed effect is due to the combined action of the two phenomena mentioned above. We are performing additional checks to better understand the physical nature of the effect, and the possible presence of numerical artifacts.

We have also developed a simple temperature model that allows us to account for the internal heating of the device. The temperature increase during device operation (present of course when some reverse current is present) affect both the transport (through the temperature dependence of donor and acceptor ionization levels and mobility) and the breakdown characteristics (via the variation with temperature of ionization rates and band gap energy). The temperatures reached by the device can be of the order of several hundreds Kelvin degrees. Such temperature raise leads in general to a reduction of the diode current.

Research plans for the remainder of the contract period

The research will continue along the following lines :

1. Comparison of the drift diffusion simulation for SiC diodes with available experiments, and identification of the mechanisms determining the device behavior at breakdown

Administrative actions during the reported period

The interaction with Dr. Fazi from ARL has continued via e-mail, since no visits have occurred. Scientific discussions have also started with Dr. Zanoni of the University of Padova, who is going to characterize some of the SiC diodes in collaboration with Dr. Fazi.

Other information

As mentioned in the 1st report, a delay exists between the actual delivery date of invoice and reports and what reported in the contract